

TOP DECOR HYBRID

Hybrid Silacrylic Plaster

03.2026 V.04

High-quality silicone-acrylic plaster, paste-like and ready to use. It is suitable for achieving a textured, decorative surface and is essential as a finishing coat in thermal insulation systems. It offers excellent adhesion, high water repellency, and its surface is protected against mold growth. It contains aggregates of various grain sizes. It is applied on surfaces such as plaster, concrete, drywall, cement board, etc. Suitable for both interior and exterior surfaces.



Stir well before use



Coverage:
2-3Kg/ m²



Drying time:
Touch dry 1 to 2 hours



Thinning
The product is ready to use



Paint:
Spatula

Product Characteristics

- Noncombustible plaster- Certified (class A2-s1, d0)
- Excellent protective and decorative properties
- Very easy to apply
- Excellent opacity
- High Adhesion
- Excellent resistance to weather condition changes
- Aesthetically pleasing finish
- Resistance to cracking
- CE Marking according to EN 15824

Shades

Available in white, base C and granulometries 1mm, 1.2mm & 1.5mm.

Packaging:

5Kg
25Kg



The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.

Technical Specifications



V.O.C.	10gr/lit (maximum Volatile Organic Compound content of ready to use product).
Density	1,82 ± 0,03 gr/cm ³ (ISO 2811).
Viscosity	Paste
pH	7-9
Coverage	2-3 kg/m ² , depending on the thickness of the film and the granulometry
Water vapour permeability	Class V ₂ (1,4m>Sd≥0,14 m -EN ISO 7783-2)
Liquid water permeability	Class W ₂ (0,5 Kg/ m ² / h ^{0,5} ≥w>0,1 Kg/ m ² / h ^{0,5} - EN 1062-3)
Adhesion	1,02 N/mm ² (EN 1542)
Thinning	No thinning is required.
Application	The product is applied by spatula.
Drying time	Touch dry 1-2 hours. (These times may be elongated depending on temperature and humidity).
Recoat	Recoat after 24 hours. (These times may be elongated depending on temperature and humidity).
Application notes	On continuous surfaces, it is recommended to use the same product batch. Different batches should be mixed and fully homogenized before use to avoid color variations.

ACCORDING TO 2004/42/EK

PHASE II ,
 Subcategory c,
 exterior walls and
 mineral substrates,
 Max VOC content
 limit value = 40gr/lit,
 max VOC content
 value = 10gr/lit
 (ready to use
 product).



Storage

Storage indoors to avoid exposure to high or low surfaces and high humidity conditions. Avoid sources of heat, radiation, static electricity, and storage near food. Keep container tightly closed. After opening can use product in a short period of time. Close the can well.



Safety Instructions- Prevention of environmental harming

Minimize paint wastage by estimating how much paint you will need. Recover unused paint for reuse. Reuse of paint can effectively minimize the products life cycle environmental impact. Clean tools with water and soap. Do not put residual paint down the kitchen sink or toilet or into a waste bin. Empty cans with paint residues should be handled the same way and disposed according to local Regulations. You should ask for advice for the local government section responsible for the collection and disposal of waste. Ask for advice from an authorized body for waste recovery. Wear protective gloves and goggles/ Do not eat, drink when handling the product. Wash wand with suitable cleaning products. Keep out of reach of children. Always read the can label before use.
For further information ask for the Safety Data Sheet of the product.

The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.

Recommended application systems

Interior/ Exterior Surfaces

• New surfaces

Preparation

Surfaces must be clean, dry, and free from grease, oils, dirt, etc. In the case of new and sound structural surfaces without issues, no special preparation is required. In the case of weak or friable surfaces, they must first be stabilized using Nature Aquafix or Nanoprimer primer.

**NATURE AQUAFIX or
NANOPRIMER**

1 COAT

Application Instructions

Prime the surface with Berling quartz-based textured primer (Quartz, Quartz Smooth, Quartz Tiles), following its application instructions.

**QUARTZ or QUARTZ
SMOOTH or QUARTZ TILES**

1 COAT

Final coating

To maximize performance, Top Décor can be overcoated with 3G Thermo Interior for interior surfaces or Monostop Vapor Elastic for exterior surfaces.

**3G THERMO INTERIOR or
MONOSTOP VAPOR ELASTIC**

1-2 COAT

• Old surfaces

Preparation

On already painted but sound surfaces without any loose or flaking areas, no special preparation is required. In the case of weak or friable surfaces, it is recommended to first sand them with sandpaper. Then, stabilize them using Nature Aquafix or Nanoprimer primer. Finally, smooth the surface with Stuco Grid, an acrylic skim-coating putty. Afterwards, stabilize again with a water-based primer such as Nature Aquafix or Nanoprimer.

**NATURE AQUAFIX or
NANOPRIMER και STUCO
GRID**

Application Instructions

Prime the surface with Berling quartz-based textured primer (Quartz, Quartz Smooth, Quartz Tiles), following its application instructions.

**QUARTZ or QUARTZ
SMOOTH or QUARTZ TILES**

1 COAT

Final coating

To maximize performance, Top Décor can be overcoated with 3G Thermo Interior for interior surfaces or Monostop Vapor Elastic for exterior surfaces.

**3G THERMO INTERIOR or
MONOSTOP VAPOR
ELASTIC**

1-2 ΕΠΙΣΤΡΩΣΕΙΣ

The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.